



## Textile Testing

553 76<sup>th</sup> Street · Byron Center, MI 49315 Phone: 616.559.6123 Fax: 616.559.6119

Report Number: 42525

Date: 09-27-2010

For the Account Of: Woven Image  
37-39 Chard road  
Brookvale 2100  
Sydney, Australia  
Contact: Sarah Long

Client's Identification: Airport 95% Wool 5% Nylon

### Test Performed California Technical Bulletin 117, Section E (CPSC 16 CFR 1610 – CS 191-53) Upholstery Fabrics

#### TEST DATA

☒ Plain Surface

☐ Raised Surface

Specimen	<u>Flame Spread</u>	<u>Flame Spread</u>
	<u>Warp Face</u> (seconds)	<u>Warp Back</u> (seconds)
1	DNI	
2	DNI	
3	DNI	
4		DNI
5		DNI

Specimen	<u>Flame Spread</u>	<u>Flame Spread</u>
	<u>Fill Face</u> (seconds)	<u>Fill Back</u> (seconds)
1	DNI	
2	DNI	
3	DNI	
4		DNI
5		DNI

#### ABBREVIATIONS USED

**DNI** Did not ignite when exposed to test ignition source

**IBE** Ignited but extinguished before burning through stop cord

**SF** Surface flash only; stop cord not burned & no burning/charring/fusing of the base fabric

**TSF** Timed surface flash; stop cord burned, but no burning/charring/fusing of the base fabric

#### ACCEPTANCE CRITERIA

1. **With nap** - Minimum flame spread of any individual specimens shall be 7 seconds.

2. **Without nap** - Minimum flame spread of any individual specimens shall be 3.5 seconds.

**CONCLUSION** Based on the above Results and Acceptance Criteria, the item tested:

☒ Complies

☐ Does Not Comply

CERTIFICATION: I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

\_\_\_\_\_  
Authorized Signature