

CSIRO ACOUSTIC MEASUREMENT REPORT

Commonwealth Scientific and Industrial Research Organisation, Infrastructure Technologies Acoustics Testing Laboratory, Research Way, Clayton, Vic 3168 Australia

Report No: AC404-02-1

Client: CSR Pty Ltd / Woven Image

376 Victoria Street, Wetherill Park, NSW, 2164

Measurement Type: Sound Absorption

AS ISO 354–2006 [R2016]: Acoustics—Measurement of sound absorption in a reverberation room

AS ISO 11654-2002 [R2016] (ISO 11654:1997): Acoustics-Rating of sound absorption-Materials and systems

Test Specimen [Specimen area⁵: 3.609 x 3.053 m (11.018 m²)]

Description: • Woven Image Embossed Panel IX 9 mm with 20 mm air gap

Panel Details3:

- Product Name: Embossed Panel IX 9 mm
- · Composition: 100 % PET (50 % recycled)
- Panel dimensions: 2800 mm x 1130 mm
- Thickness: 9 mm + 7%
- Profile: corrugated with 49 mm pitch, 5 mm thick at valleys, 9 mm thick at peaks
- Area density: 2385 g/m² ± 10%

- The reverberation chamber was swept and vacuumed in preparation for specimen installation.
- The specimen consisted of 2 uncut panels, 1 full-length panel cut to 0.74 m width, 2 full-width panels cut to 0.8 m length and 1 panel cut to 0.74 x 0.8 m. These were arranged in a rectangle at an angle of 6° from the nearest chamber wall (not parallel, as per AS ISO 354 cl 6.2.1.2). All corrugations were aligned in the same direction.
- . The panels were suspended 20 mm above the chamber floor on a randomly arranged array of spacers creating no interior partitions. The number of spacers was minimised whilst preventing excessive sagging of the panels, maintaining the air gap.
- The exposed perimeter edges of the specimen were covered with a skirt of 1 mm thick folded steel angle, 40 mm high. The installation minimised panel-panel and panel-skirt gaps.
- The perimeter of the skirt was taped to the chamber floor.
- · Specimen installation was carried out by laboratory staff.



Test specimen installed in laboratory for test



Side view of panel suspended by 20 mm prior to skirt installation

Measurement Details & Results						1.0	
Freq	Absorption coefficients			Reverberation times, T ₆₀ (sec)			——— C(s (1/3-Octave)
Hz	α_s	α_{p}	95% Conf (δ)	Empty room ⁴	with Specimen		 α_p (whole Octave)
100	0.01		0.04	4.55	4.48		Cw 0.40 Reference line
125	0.03	0.05	0.03	5.66	5.37	0.8	OW 0.40 INGIGIENCE INTE
160	0.04		0.03	6.11	5.59		
200	0.06		0.03	5.28	4.78		♥
250	0.11	0.10	0.04	4.57	3.90		
315	0.17		0.03	5.61	4.27	0.6	
400	0.24		0.04	5.59	3.83		
500	0.39	0.40	0.04	5.13	3.08		<u> </u>
630	0.51		0.04	4.63	2.58		
800	0.60		0.03	4.53	2.36	0.4	
1000	0.68	0.70	0.03	4.46	2.20		
1250	0.79		0.04	4.11	1.96		
1600	0.84		0.04	3.57	1.77		/ X
2000	0.84	0.85	0.04	3.28	1.70	0.2	
2500	0.82		0.04	2.87	1.60		
3150	0.81	0.00	0.05	2.54	1.50		
4000	0.82	0.80	0.03	2.07	1.31		. ◆ × ×
5000	0.83		0.04	1.66	1.14	0.0	
Performance Indices ^{1,2}							Measurement Conditions

Performance Indices 1,2

 $\alpha_{W} = 0.40 \, (MH)$ SAA = 0.50NRC = 0.50

The required 12 spatially independent decay curves came from ensemble averaging 10 successive decays with each of 3 different source loudspeaker positions, all sampled by 4 fixed microphones, using linear averaging

Date of measurement: Temperature & humidity: Atmospheric pressure

Empty room 5 Sep 2025 17 °C, 48 % R.H. 1017 mbar

with Test Specimen 5 Sep 2025 17 °C, 48 % R.H. 1016 mbar

Sound Absorption Class = D Notes, Deviations etc

- 1. Shape indicators (L, M, and H), if any, following the αw index, indicate α_p values above the reference contour by ≥ 0.25 in the Low, Medium or High frequency ranges respectively; it is strongly recommended to use this single number rating in combination with the complete sound absorption coefficient curve.
- 2. SAA and NRC are defined in ASTM C423; laboratory requirements for which differ from AS ISO 354.
- 3. Material details stated are as per client advice; unless identified as (meas), indicating measured by CSIRO.
- Empty room absorption in the 100, 250 and 800 Hz bands did not meet all AS ISO 354 requirements; a noncompliance unrelated to the product/material under test.
- Specimen area used in calculations (11.018 m²) was the area inside the steel angle enclosing the installed panels

Issuing Authority

Signed: Jim Payne Date 7 October 2025

Instrumentation

Real time analyser: • Brüel & Kjær PULSE LAN-XI type 3160-A-042

Microphones/preamps: • 4 x GRAS 46AQ microphone/preamps sets, in fixed positions as per **AS ISO 354**

Noise source: • Room populated with three Norsonic NOR276 dodecahedron

loudspeakers, driven in turn by a Norsonic NOR280 power amplifier.

Calibration: • Analyser: Feb 2025 (DANAK cal, ilac-MRA recognised)

Laboratory Construction

Reverb room: • 300 mm thick concrete (closed off from the adjoining room by a composite wall) • parallelepiped with dimensional proportions 1:1.3:1.6 for distribution of room modes • approx. 202 m3 total room volume

approx. 215 m² surface area excluding diffusers

Diffusers: • 20 stationary diffusers, approx. 40 m² total surface area Absorption area: • in accordance with AS ISO 354, unless noted otherwise4

Legal Information and Disclaimer Copyright @ 2025 CSIRO. To the extent permitted by law, CSIRO (including its employees and consultants) excludes all liability to any person for any consequences, including but not limited to all losses, damages, costs, expenses and any other compensation, arising directly or indirectly from using any information or material contained in this document. Reports relate only to items tested. No alterations permitted. This report may be distributed only in its entirety. Page 1 of 1