

**Textile Testing**553 76th Street · Byron Center, MI 49315 Phone: 616.559.6123 Fax: 616.559.6119

TESTING CERT. #3193.01

Report Number: 57935

Date: 04-12-2013

For the Account Of: Woven Image Pty Ltd.
37-39 Chard rd, Brookvale NSW 2100
Australia
Contact: Amy Saunders

Client's Identification: Mono CR with Crypton

Test Performed California Technical Bulletin 117, Section E (CPSC 16 CFR 1610 – CS 191-53) Upholstery Fabrics, March 2000

TEST DATA☒ Plain Surface☐ Raised Surface

Specimen	Flame Spread	Flame Spread
	<u>Warp Face</u> (seconds)	<u>Warp Back</u> (seconds)
1	DNI	
2	DNI	
3	DNI	
4		DNI
5		DNI

Specimen	Flame Spread	Flame Spread
	<u>Fill Face</u> (seconds)	<u>Fill Back</u> (seconds)
1	DNI	
2	DNI	
3	DNI	
4		DNI
5		DNI

ABBREVIATIONS USED

DNI Did not ignite when exposed to test ignition source
IBE Ignited but extinguished before burning through stop cord
SF Surface flash only; stop cord not burned & no burning/charring/fusing of the base fabric
TSF Timed surface flash; stop cord burned, but no burning/charring/fusing of the base fabric

ACCEPTANCE CRITERIA

- 1. With nap** - Minimum flame spread of any individual specimens shall be 7 seconds. (ACT Criteria decreases minimum time to 4 seconds)
- 2. Without nap** - Minimum flame spread of any individual specimens shall be 3.5 seconds.

CONCLUSION Based on the above Results and Acceptance Criteria, the item tested:

☒ Complies☐ Does Not Comply

CERTIFICATION: I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature-MB