



**FIRE  
TECHNOLOGY  
SERVICES**

**Wira House  
West Park Ring Road  
Leeds, LS16 6QL  
England**

Tel: +44 (0)113 259 1999  
Fax: +44 (0)113 278 0306  
Web: <http://www.bttg.co.uk>  
Email: [CSLeeds@bttg.co.uk](mailto:CSLeeds@bttg.co.uk)

Our Ref: 2702235/04/11  
Your Ref:  
Order No:

11 April 2011  
Page 1 of 5

Client: Woven Image PTY Ltd  
37-39 Chard Road  
Brookvale  
NSW 2100  
Australia

Job Title: **Fire Test on One Sample of Fabric**

Material Received: 1 April 2011

Description of Sample: One sample of fabric, referenced: **Global, 100% Polyester.**

Brief: Fire Technology Services were requested to carry out a fire test on the sample supplied to BS EN 1021-1/2.

UKAS Accreditation: Our Laboratories are UKAS accredited. However, it should be noted that tests marked \* are not UKAS accredited in this report. They are not included in the UKAS Accreditation Schedule for our laboratory, either due to the work not conforming fully to the standard (e.g. reduced number of specimens) or to it being outside the scope of our accreditation, or subcontracted.

Uncertainty: An estimation of uncertainty of measurement has not been taken into account when making a judgement to any pass/fail criteria.



Woven Image PTY Ltd

**FIRE TESTS ACCORDING TO BS EN 1021-1:2006**

**Assessment of the ignitability of upholstered furniture. Part I. Ignition Source : Smouldering cigarette. (BS 5852:1990 Section 4. As amended 1994) (ISO 8191-1987 modified)**

**Date of Test: 08/04/2011**

**Conditioning**

The sample was water-soaked in accordance with this standard and immediately prior to testing the sample was conditioned for at least 16 hours at a temperature of  $23 \pm 2^\circ\text{C}$  and relative humidity of  $50 \pm 5\%$ .

The sample was tested in a room of volume  $25\text{m}^3$  and  $20^\circ\text{C}$ .

**Procedure**

The test was carried out in accordance with BS EN 1021-1. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The specimens were mounted over fillings of combustion modified high resilience foam of density about  $35\text{kg/m}^3$ .

Tests were made using ignition source 0 in accordance with paragraph 9 of the above standard.

**Requirements**

The specimens shall not:-

- a) display escalating combustion requiring active extinction.
- b) smoulder or burn until it is essentially consumed within the test duration.
- c) smoulder or burn to the extremities of the specimen, or through the full thickness, within the duration of the test.
- d) smoulder for more than one hour.
- e) show evidence of charring, other than discolouration, for more than 100mm in any direction apart from the nearest part of the original position of the source.



Woven Image PTY Ltd

Results

	Cigarette		Comments
	1	2	
<b>Smouldering Criteria (Yes/No)</b>			
Unsafe escalating combustion	No	No	
Test assembly consumed	No	No	
Smoulders to extremities	No	No	
Smoulders through thickness	No	No	
Smoulders more than 1 hour	No	No	
More than 100mm from source	No	No	
<b>Ignitability Performance (Yes/No)</b>			
Unsafe escalating combustion	N/A	N/A	
Test assembly consumed	N/A	N/A	
Flames to extremities	N/A	N/A	
Flames through thickness	N/A	N/A	
Ignition / Non Ignition ( I/NI )	NI	NI	

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Comments

A NI designation indicates that the sample met the performance requirements.

