

# DAVID J HEFFER AND ASSOCIATES

Consulting Textile  
Technologists

22 Hicks Street, Lara, Vic, 3212  
Tel: (03) 5282 1337

djheffer@djha.com.au  
www.djha.com.au

ABN. 87 710 470 062



## LABORATORY REPORT

Date : 20 February 2025

Report Number: 258757

Client: WOVEN IMAGE PTY LIMITED  
37-39 CHARD ROAD  
BROOKVALE NSW 2100

Reference: Harry Vasey

Sample: EchoPanel, 12mm and 24mm

### Results:

Luminous reflectance (ASTM E1477-98A: 2017)

Sample	Thickness (mm)	Colour No	Colour Name	Luminous Reflectance
1	12	106	Butter	69.31
2	12	124	Ochre	36.09
3	12	167	Cinnamon	14.44
4	12	193	Rouge	10.94
5	12	274	Orchid	38.14
6	12	295	Mandarin	20.07
7	12	338	Jade	20.52
8	12	349	Vinyard	16.76
9	12	365	Navy	8.04
10	12	381	Lime Splice	69.31
11	12	384	Olive	17.60
12	12	402	Pebble	21.25
13	12	444	Smoke	20.09
14	12	447	Slate	11.88
15	12	454	Mushroom	52.03
16	12	468	Vanilla	42.59
17	12	484	Cayenne	13.75
18	12	487	Blush	40.06
19	12	495	Dusk	41.16
20	12	551	Duck Egg	35.67
21	12	573	Mint	54.87
22	12	579	Pistachio	33.98

Laboratory Report  
258757  
Woven Image Pty Limited

Sample	Thickness (mm)	Colour No	Colour Name	Luminous Reflectance
23	12	580	Sage	32.77
24	12	660	Coronet	19.07
25	12	721	Nutmeg	26.62
26	12	908	Cream	60.13
27	24	269	Wine	7.34
28	24	330	Ivy	7.30
29	24	550	Onyx	2.76
30	24	633	Pacific	20.38



DAVID J HEFFER  
DIRECTOR