



BRANZ Technical Opinion

FC12885-001

ASSESSMENT REPORT ON THE FIRE PERFORMANCE OF WOVEN IMAGE MURA AND ECHOPANEL®

CLIENT

Woven Image Pty Ltd
37-39 Chard Road
Brookvale 2100
New South Wales
Australia



REPORT NUMBER:

FC12885-001

ISSUE DATE:

2 June 2020

PAGE:

1 of 8

THE LEGAL VALIDITY OF THIS REPORT CAN ONLY BE CLAIMED ON PRESENTATION OF THE COMPLETE SIGNED PAPER REPORT.
EXTRACTS OR ABRIDGMENTS OF THIS REPORT SHALL NOT BE PUBLISHED WITHOUT PERMISSION FROM BRANZ LTD.

ASSESSMENT OBJECTIVE

This report gives BRANZ's assessment of the fire performance in accordance with the Building Code of Australia (NCC Specification C1.10 Clause 4, determined in accordance with AS 5637.1) in respect to the fire performance of Woven Image Mura (1.9 mm), EchoPanel® 7 mm, and EchoPanel® 12 mm. All are 100% PET (60% recycled) polyester fibre wall panels of nominal thickness 1.9 mm, 7 mm, 12 mm, and weight 350 gsm, 1,400 gsm, 2,400 gsm, respectively.

CLIENT

Woven Image Pty Ltd
37-39 Chard Road
Brookvale 2100
New South Wales
Australia

CONCLUSION

It is considered that on the basis of the performance of Woven Image EchoPanel® 24 mm, 100% polyester fabric with 3,000 gsm weight as tested in BRANZ ISO room test FI 12432-001, that similar product of the same composition, lesser thickness and weight and therefore less potential heat release, known as Woven Image Mura (1.9 mm), EchoPanel® 7 mm, and EchoPanel® 12 mm, polyester fibre wall panels with weight 350 gsm, 1,400 gsm, and 2,400 gsm are likely to achieve the same result if tested in accordance with AS ISO 9705:2003 (R 2016).

| Building Code Document | Group Number Classification |
|---|--|
| NCC Volume One Specification C1.10 Clause 4 determined in accordance with AS 5637.1 | 1 The SMOGRA was not more than the 100 m ² /s ² x 100 limit |

LIMITATION

This report is subject to the accuracy and completeness of the information supplied.

BRANZ reserves the right to amend or withdraw this assessment if information becomes available which indicates the stated fire performance may not be achieved.

This assessment report may only be quoted or reproduced in full.

| | | | |
|---|--------------------------------------|-----------------------------------|------------------------|
|  | REPORT NUMBER: FC12885-001 | ISSUE DATE: 2 June 2020 | PAGE: 2 of 8 |
|---|--------------------------------------|-----------------------------------|------------------------|

THE LEGAL VALIDITY OF THIS REPORT CAN ONLY BE CLAIMED ON PRESENTATION OF THE COMPLETE SIGNED PAPER REPORT.
EXTRACTS OR ABRIDGMENTS OF THIS REPORT SHALL NOT BE PUBLISHED WITHOUT PERMISSION FROM BRANZ LTD.

TERMS AND CONDITIONS

This report is issued in accordance with the Terms and Conditions as detailed and agreed in BRANZ Services Agreement for this work.

The results reported here relate only to the item/s described in this report.



REPORT NUMBER:

FC12885-001

ISSUE DATE:

2 June 2020

PAGE:

3 of 8

THE LEGAL VALIDITY OF THIS REPORT CAN ONLY BE CLAIMED ON PRESENTATION OF THE COMPLETE SIGNED PAPER REPORT.
EXTRACTS OR ABRIDGMENTS OF THIS REPORT SHALL NOT BE PUBLISHED WITHOUT PERMISSION FROM BRANZ LTD.

CONTENTS

| | |
|---------------------------------------|----------|
| SIGNATORIES | 5 |
| DOCUMENT REVISION STATUS | 5 |
| 1. INTRODUCTION | 6 |
| 2. BACKGROUND | 6 |
| 3. DISCUSSION..... | 7 |
| 4. CONCLUSION..... | 8 |

TABLES

| | |
|--|---|
| Table 1: Test results in FI 12432-001 | 6 |
| Table 2: Physical properties of Woven Image Mura and EchoPanel® | 7 |
| Table 3: Assessed ISO room result for Woven Image Mura (1.9 mm), EchoPanel® 7 mm, and EchoPanel® 12 mm | 8 |



REPORT NUMBER:

FC12885-001

ISSUE DATE:

2 June 2020

PAGE:

4 of 8

THE LEGAL VALIDITY OF THIS REPORT CAN ONLY BE CLAIMED ON PRESENTATION OF THE COMPLETE SIGNED PAPER REPORT.
EXTRACTS OR ABRIDGMENTS OF THIS REPORT SHALL NOT BE PUBLISHED WITHOUT PERMISSION FROM BRANZ LTD.

SIGNATORIES



Author

L. F. Hersche
Fire Testing Engineer
BRANZ



Reviewer

E. Soja
Senior Fire Safety Engineer
BRANZ

DOCUMENT REVISION STATUS

| ISSUE NO. | DATE ISSUED | DESCRIPTION |
|-----------|-------------|---------------|
| 001 | 2 June 2020 | Initial Issue |



REPORT NUMBER:

FC12885-001

ISSUE DATE:

2 June 2020

PAGE:

5 of 8

THE LEGAL VALIDITY OF THIS REPORT CAN ONLY BE CLAIMED ON PRESENTATION OF THE COMPLETE SIGNED PAPER REPORT.
EXTRACTS OR ABRIDGMENTS OF THIS REPORT SHALL NOT BE PUBLISHED WITHOUT PERMISSION FROM BRANZ LTD.

1. INTRODUCTION

This report gives the BRANZ assessment of the Group Number classification for the Woven Image products listed below:

- Woven Image Mura (1.9 mm)
- Woven Image EchoPanel® 7 mm
- Woven Image EchoPanel® 12 mm

2. BACKGROUND

In BRANZ ISO room test FI 12432-001 the product submitted for testing by the client was identified by the client as Woven Image EchoPanel® 24 mm 100% PET (60% recycled) polyester fibre with thickness 24 mm and nominal weight of 3,000 gsm.

The polyester panel was adhered to nominally 6 mm fibre cement substrate with H.B. Fuller Max Bond Fast Grip around the perimeter of each panel and at vertical 200 mm centres.

The results of the test in accordance with AS ISO 9705 determined in accordance with AS 5637.1 are shown in Table 1.

Table 1: Test results in FI 12432-001

| Building Code Document | Group Number Classification |
|---|--|
| NCC Volume One Specification C1.10 Clause 4 determined in accordance with AS 5637.1 | 1 The SMOGRA was not more than the 100 m ² /s ² x 100 limit |
| NZBC Verification Method C/VM2 Appendix A | 1-S Average Smoke Production Rate was less than the 5 m ² /s limit |



REPORT NUMBER:

FC12885-001

ISSUE DATE:

2 June 2020

PAGE:

6 of 8

THE LEGAL VALIDITY OF THIS REPORT CAN ONLY BE CLAIMED ON PRESENTATION OF THE COMPLETE SIGNED PAPER REPORT.
EXTRACTS OR ABRIDGMENTS OF THIS REPORT SHALL NOT BE PUBLISHED WITHOUT PERMISSION FROM BRANZ LTD.

3. DISCUSSION

In addition to the tested product as reported above which is known as Woven Image EchoPanel® with thickness 24 mm and weight 3,000 gsm, the test result may also be applied to the following variation of the same product as listed below:

- Woven Image Mura (1.9 mm)
- Woven Image EchoPanel® 7 mm
- Woven Image EchoPanel® 12 mm

The physical parameters were provided by the client for Woven Image Mura (1.9 mm), EchoPanel® 7 mm, and 12 mm thicknesses and are shown in Table 2.

Table 2: Physical properties of Woven Image Mura and EchoPanel®

| Nominal Thickness (mm) | Weight (gsm) | Density (kg/m³) |
|------------------------|--------------|-----------------|
| 1.9 mm | 350 | 184.2 |
| 7 mm | 1,400 | 200.0 |
| 12 mm | 2,400 | 200.0 |

Comparing the nominal 24 mm thick Woven Image EchoPanel® tested in BRANZ ISO room test FI12432-001 with the assessed nominal 1.9 mm, 7 mm, and 12 mm Woven Image Mura and EchoPanel® the weight in gsm is less than the 24 mm sample by 88%, 53%, and 20% respectively.

On the basis that for identical product composition and where the thickness and weight is reduced compared with the product that was tested, then it follows that the quantity of combustible material is also reduced and therefore the Group Number and Smoke Production Rate (SPR) as tested in the BRANZ ISO room test FI 6050 is unlikely to be prejudiced.



REPORT NUMBER:

FC12885-001

ISSUE DATE:

2 June 2020

PAGE:

7 of 8

THE LEGAL VALIDITY OF THIS REPORT CAN ONLY BE CLAIMED ON PRESENTATION OF THE COMPLETE SIGNED PAPER REPORT.
EXTRACTS OR ABRIDGMENTS OF THIS REPORT SHALL NOT BE PUBLISHED WITHOUT PERMISSION FROM BRANZ LTD.

4. CONCLUSION

It is considered that on the basis of the performance of Woven Image EchoPanel® 24 mm, 100% polyester fabric with 3,000 gsm weight as tested in BRANZ ISO room test FI 12432-001, that similar product of the same composition, lesser thickness and weight and therefore less potential heat release, known as Woven Image Mura (1.9 mm), EchoPanel® 7 mm, and EchoPanel® 12 mm, polyester fibre wall panels with weight 350 gsm, 1,400 gsm, and 2,400 gsm are likely to achieve the same result if tested in accordance with AS ISO 9705:2003 (R 2016), as shown in Table 3.

Table 3: Assessed ISO room result for Woven Image Mura (1.9 mm), EchoPanel® 7 mm, and EchoPanel® 12 mm

| Building Code Document | Group Number Classification |
|---|--|
| NCC Volume One Specification C1.10 Clause 4 determined in accordance with AS 5637.1 | 1 The SMOGRA was not more than the 100 m ² /s ² x 100 limit |



REPORT NUMBER:

FC12885-001

ISSUE DATE:

2 June 2020

PAGE:

8 of 8

THE LEGAL VALIDITY OF THIS REPORT CAN ONLY BE CLAIMED ON PRESENTATION OF THE COMPLETE SIGNED PAPER REPORT.
EXTRACTS OR ABRIDGMENTS OF THIS REPORT SHALL NOT BE PUBLISHED WITHOUT PERMISSION FROM BRANZ LTD.