

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N. 43 006 014 106  
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O. Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

CLIENT : WOVEN IMAGE PTY LTD  
37-39 CHARD ROAD  
BROOKVALE NSW 2100

TEST NUMBER : 7-571073-BN  
ISSUE DATE : 11/02/2010  
PRINT DATE : 11/02/2010

SAMPLE DESCRIPTION Clients Ref: "Outdoor Fine"  
Woven fabric  
Approximate thickness: 1mm  
Colour: Green/Brown  
End Use: Indoor/Outdoor Commercial Upholstery

THESE RESULTS MUST BE CONSIDERED IN CONJUNCTION  
WITH THE COMMENTS ON THE FOLLOWING PAGE(S)

Material Specification provided by client:  
Nominal composition: 100% Polyolefin  
Nominal mass: 310g/lin.m

AS/NZS 1530.3 - 1999 Simultaneous determination of Ignitability, Flame  
Propagation, Heat Release and Smoke Release

RESULTS:

Face tested: Face

Date tested: 10.02.2010

	Mean		Standard Error
Ignition time	7.72	min	0.25
Flame propagation time	Nil	s	Nil
Heat release integral	52.7	kJ/m <sup>2</sup>	2.5
Smoke release, log d	-1.4884		0.0888
Optical density, d	0.0358	/m	

Number of specimens ignited: 6

Number of specimens tested: 6

REGULATORY INDICES: Ignitability Index 12 Range 0-20  
Spread of Flame Index 0 Range 0-10  
Heat Evolved Index 2 Range 0-10  
Smoke Developed Index 3 Range 0-10

Comments:

These results only apply to the specimen mounted, as described in this report.

The results of this fire test may be used to directly assess fire hazard, but it should be recognized that a single test method will not provide a full assessment of fire hazard under all fire conditions.

The reaction of thin unsupported flexible materials to flame impingement can be assessed in accordance with AS 1530.2. Where materials of thickness less than 2mm that are sufficiently flexible to be bent by hand around a mandrel of 2mm diameter or less are subjected to the test described herein, they should also be subjected to the test in AS 1530.2.

179244

1

CONTINUED NEXT PAGE

PAGE 1

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:  
-Chemical Testing of Textiles & Related Products : Accreditation No. 983  
-Mechanical Testing of Textiles & Related Products : Accreditation No. 985  
-Heat & Temperature Measurement : Accreditation No. 1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.



*Jandolac*

APPROVED SIGNATORY

*Michael A. Jackson*  
MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N. 43 006 014 106  
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O. Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

CLIENT : WOVEN IMAGE PTY LTD  
37-39 CHARD ROAD  
BROOKVALE NSW 2100

TEST NUMBER : 7-571073-BN  
ISSUE DATE : 11/02/2010  
PRINT DATE : 11/02/2010

Each test specimen had an unattached backing of 4.5mm thick fibre reinforced cement board.

The specimens melted away from the area of maximum heat and produced flaming droplets during the test. Due to this phenomena it should be recognised that this test result may not be a true indication of the product's fire hazard properties.

Each test specimen was restrained on the exposed face by a layer of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal spacing 12mm in both directions and securely fixed to a backing board at four points each 100mm from the centre of the sample and the assembly clamped in four places.

To allow free movement of sample during testing all corners were folded away from the clamps.

179244

1

( END OF REPORT )

PAGE 2

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:  
-Chemical Testing of Textiles & Related Products : Accreditation No. 983  
-Mechanical Testing of Textiles & Related Products : Accreditation No. 985  
-Heat & Temperature Measurement : Accreditation No. 1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR