

Wira House West Park Ring Road Leeds, LS16 6QL England

Tel: +44 (0)113 259 1999 Fax: +44 (0)113 278 0306 Web:http://www.bttg.co.uk Email:CSLeeds@bttg.co.uk

Our Ref: 27/02013A/06/10 Your Ref: Order No:

28 June 2010 Page 1 of 5

Client:	Woven Image PTY Ltd 37-39 Chard Road Brookvale New South Wales 2100 Australia
Job Title:	Fire Test
Material Received:	11 June 2010
Description of Sample:	One sample of fabric, referenced: Airport, 95% Wool, 5% Nylon, 137cm, 616.5g/lin.m, 450g/m <sup>2</sup> Primary Use Commercial Upholstery.
Brief:	Fire Technology Services were requested to carry out a fire test on the sample supplied to BSEN 1021 Part 1 and 2.

UKAS Accreditation: Our Laboratories are UKAS accredited. However, it should be noted that tests marked \* are not UKAS accredited in this report. They are not included in the UKAS Accreditation Schedule for our laboratory, either due to the work not conforming fully to the standard (e.g. reduced number of specimens) or to it being outside the scope of our accreditation, or subcontracted. Uncertainty: An estimation of uncertainty of measurement has not been taken into account when making a judgement to any pass/fail criteria.



FTS is a business centre of BTTG Testing & Certification Ltd,

Unit 14, Wheel Forge Way, Ashburton Road West, Trafford Park, Manchester M17 1EH, Company No. 04669650 The supply of all goods and services is subject to our conditions of sale, copies of which are available from our web site - http://www.bttg.co.uk/pdfs/Terms\_Conditions.pdf



Date: 28 June 2010 Our Ref: 27/02013A/06/10 Your Ref: Order No: Page 2 of 5

Woven Image PTY Ltd

## FIRE TESTS ACCORDING TO BS EN 1021-1 2006

Assessment of the ignitability of upholstered furniture. Part I. Ignition Source : Smouldering cigarette. (BS 5852:1990 Section 4. As amended 1994) (ISO 8191-1987 modified)

### Date of Test: 24/06/10

## Conditioning

The sample was water-soaked in accordance with this standard and Immediately prior to testing the sample was conditioned for at least 16 hours at a temperature of  $23\pm2$  C and relative humidity of  $50\pm5\%$ .

The sample was tested in a room of volume 25m<sup>3</sup> and 20°C.

## Procedure

The test was carried out in accordance with BS EN 1021-1. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The specimens were mounted over fillings of standard non-FR polyure thane foam of density about  $22 \text{Kg/m}^3$ .

Tests were made using ignition source 0 in accordance with paragraph 9 of the above standard.

### Requirements

The specimens shall not:-

- a) display escalating combustion requiring active extinction.
- b) smoulder or burn until it is essentially consumed within the test duration.
- c) smoulder or burn to the extremities of the specimen, or through the full thickness, within the duration of the test.
- d) smoulder for more than one hour.
- e) show evidence of charring, other than discolouration, for more than 100mm in any direction apart from the nearest part of the original position of the source.





Date: 28 June 2010 Our Ref: 27/02013A/06/10 Your Ref: Order No: Page 3 of 5

Woven Image PTY Ltd

#### Results

	Cigarette		Commonto
	1	2	Comments
Smouldering Criteria (Yes/No)			
Unsafe escalating combustion	No	No	
Test assembly consumed	No	No	
Smoulders to extremities	No	No	
Smoulders through thickness	No	No	
Smoulders more than1 hour	No	No	
More than 100mm from source	No	No	
Ignitability Performance (Yes/No)			
Unsafe escalating combustion	No	No	
Test assembly consumed	No	No	
Flames to extremities	No	No	
Flames through thickness	No	No	
Ignition / Non Ignition ( I/NI )	NI	NI	

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

### Comments

A NI designation indicates that the sample met the performance requirements.





Date: 28 June 2010 Our Ref: 27/02013A/06/10 Your Ref: Order No: Page 4 of 5

Woven Image PTY Ltd

# FIRE TESTS ACCORDING TO BS EN 1021-2 2006

Assessment of the ignitability of upholstered furniture. Part 2. Ignition Source : Match flame equivalent. (BS 5852:1990 Section 4. As amended 1994) (ISO 8191-2 1988 modified)

## Date of Test: 24/06/10

# Conditioning

The sample was water-soaked in accordance with this standard and Immediately prior to testing the sample was conditioned for at least 16 hours at a temperature of  $23\pm2$  C and relative humidity of  $50\pm5\%$ .

The sample was tested in a room of volume 25m<sup>3</sup> and 20°C.

## Procedure

The test was carried out in accordance with BS EN 1021-2. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The specimens were mounted over fillings of standard non-FR polyure thane foam of density about  $22 \text{Kg/m}^3$ .

Tests were made using ignition source 1 in accordance with paragraph 9 of the above standard.

### Requirements

The specimens shall not:-

- a) display escalating combustion requiring active extinction.
- b) smoulder or burn until it is essentially consumed within the test duration.
- c) smoulder or burn to the extremities of the specimen, or through the full thickness, within the duration of the test.
- d) smoulder for more than one hour.
- e) show evidence of charring, other than discolouration, for more than 100mm in any direction apart from the nearest part of the original position of the source.
- f) burn for more than 120s after removal of the burner tube.





Date: 28 June 2010 Our Ref: 27/02013A/06/10 Your Ref: Order No: Page 5 of 5

Woven Image PTY Ltd

#### Results

	Match Flame		
	Equivalent		Comments
	1	2	
Smouldering Criteria (Yes/No)			
Unsafe escalating combustion	No	No	
Test assembly consumed	No	No	
Smoulders to extremities	No	No	
Smoulders through thickness	No	No	
Smoulders more than 1 hour	No	No	
More than 100mm from source	No	No	
Ignitability Performance (Yes/No)			
Unsafe escalating combustion	No	No	
Test assembly consumed	No	No	
Flames to extremities	No	No	
Flames through thickness	No	No	
Flames longer than120 seconds	No	No	
Ignition / Non Ignition ( I/NI )	NI	NI	

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

### Comments

A NI designation indicates that the sample met the performance requirements.

The information contained on page no's 1/5 of this certificate is hereby certified to be a correct statement of the tests and investigations carried out by FTS on the materials referred to.

Signed	Date. 30 June 2010
Mrs B Marsden	
Fire Technician	
Reported By	Date.30 June 2010

P Doherty Operational Head

