

Mura Haku & Kome

Designer: Akira Isogawa in collaboration with Woven Image

Application(s): Workstations, Walls, Partitions

Composition & Pattern

Composition 100% PET (60% post-consumer recycled)

Colours Available 4

Weave Non woven

Pattern Type Printed

Printed Sides Single

Pattern Repeat Horizontal: 14.5cm, Vertical: 20cm

Dimensions & Weight

Dimensions Length: 25m, Width: 1210mm (+/- 5mm), Thickness: 1.9mm (+/- 0.25mm) Also available in lengths of 6m

Unit of Sale Linear metre

Unit of Sale Net Weight (kg) 0.424

Performance

Fire Test Result ASTM E84 Adhered: Class 1 or A, BS 476: Class 2, BS EN 13501.1:

Classification B - s1, d0, BS EN 45545-2 + A1 Annex C: CIT: 0.00,
ISO 9705: Group 1

Acoustic Performance Standard Test Method	AS ISO 354: 2006 (R2016)
Noise Reduction Coefficient (NRC) Result	Direct fix: 0.10
Sound Absorption Average (SAA) Result	Direct fix: 0.08
Weighted Sound Absorption Coefficient (α_w) Result	Direct fix: 0.10 (H)
Additional Acoustic Information	Noise reduction coefficient result key: H = High Frequency / MH = Mid to High Frequency
Colour Fastness to Light Standard Test Method	ISO 105 B02
Colour Fastness Light Rating	6
Colour Fastness to Rubbing Standard Test Method	ISO 105 - X12
Colour Fastness to Rubbing Rating	Wet: 5, Dry: 5

Sustainability

VOC Emissions Results Mura Haku achieves ASTM D5116: TVOC Emissions Rate: $<0.031\text{mg}/\text{m}^2/\text{hr}$ (7 days), and Mura Kome achieves ASTM D5116: TVOC Emissions Rate: $<0.02\text{mg}/\text{m}^2/\text{hr}$ (7 days)

Sustainability Performance



Instructions

Additional Information See Woven Image Mura Installation Guide.

Exact colour matching cannot be guaranteed between batches. Fibre mix and web variation are natural characteristics of this product.