


Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Woven Imag 37-39 Chard								
Brookvale N		Issue Date Print Date	: 28/11/201 : 28/11/201					
				-				
Sample Description	Clients Ref : "Edge 111"							
	Woven Fabric							
	Colour: Taupe							
	End Use : Upholstery, Wrapped Panels							
	Nominal Composition : 100% Polyester							
SEN 1021-1-2006	Furniture - Assessment of the Ignitability of Upholstered Furniture Part 1: Ignition Source - Smouldering Cigarette							
	Date of Testing		27/11/2019					
	Did Ignition Occur		No					
	Did Ignition Occur Extent of Damage	Vertical	No Horizontal					
	-	Vertical 6		mm				
	Extent of Damage		Horizontal	mm mm				
	Extent of Damage Length	6	Horizontal 4					
	Extent of Damage Length Width	6 6	Horizontal 4 3	mm				
	Extent of Damage Length Width Depth	6 6	Horizontal 4 3 4	mm mm				
	Extent of Damage Length Width Depth Ignition Source Time	6 6	Horizontal 4 3 4 9.75	mm mm min				
	Extent of Damage Length Width Depth Ignition Source Time Flame Time	6 6	Horizontal 4 3 4 9.75 0.0	mm mm min min				

The above test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use.



MANAGING DIRECTOR

(C)

В



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client :	Woven Image Pty Ltd	Test Number	:	19-006739
	37-39 Chard Road	Issue Date	:	28/11/2019
	Brookvale NSW 2100	Print Date	:	28/11/2019

BSEN 1021.2-2006 (Modified)

Furniture - Assessment of the Ignitability of Upholstered Furniture Part 2: Ignition Source - Match Flame Equivalent

Date of Testing		27/11/2019	
Did Flaming Ignition Occur?		Yes	
Did Smouldering Ignition Occur?		No	
Extent of Damage	Vertical	Horizontal	
Length	450	450	mm
Width	280	300	mm
Depth	75	75	mm
Time for Burning to reach Rig Extremities		4.50	min
Test Assembly Self Extinguished	No		
Assembly Smouldering when Dismantled	No		

The above test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

Modification: Propane/Butane mixture used as ignition source.

187227

40566





the Managing Director of AWTA Ltd.

Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing Mechanical Testing Performance & Approvals Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by

: Accreditation No Accreditation No : Accreditation No

983 985 1356

Page 2 of 2



APPROVED SIGNATORY