



DOTTIE
CAL 117

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: testing@govmark.com

Page 1

Received: 01/25/2018	Completed: 01/26/2018	Letter: S2	BG	P.O.#: 18-0066208	Test Report #: 3-24249-0-02
----------------------	-----------------------	------------	----	-------------------	-----------------------------

Client's Identification	Style: K2259 Cationc. Content: 30% Polyester, 70% Post Consumer Recycled Polyester. Finish: Greenshield & Acrylic Backing: Weight: 23 oz/ly. End Use: Upholstery
-------------------------	---

Tested For: Sandra L. Gerloff Knoll Inc. 1235 Water Street E Greenville, PA 18041	Key Test: CA TB 117-2013 (Section 1-Cover Fabric) /ACT Tel: 1-(215)-679-1765 Fax: 1-(215)-679-1600	235 Ext:
---	--	-------------

Test Category: Cigarette Ignition	Specifier: ACT	LE 2015; V 08/15	NTR 9/15
Product Category: Upholstery	PC: 24H	d1/SM	

TEST PERFORMED: California Technical Bulletin 117-2013 - Requirements, Test Procedure and Apparatus for Testing the Smolder Resistance of Materials Used in Upholstered Furniture (June 2013 Version)

Section 1, Cover Fabric Test (Upholstery cover material is the outermost layer of fabric or related material used to enclose the main support system or upholstery materials, or both, used in the furniture item.) --

As cited by the ACT Voluntary Performance Guidelines (January 2015)

REFERENCE: ASTM E1353-08a e1

IGNITION SOURCE: SRM 1196 Cigarette

SPECIMEN TEST COMPOSITE:

Upholstery Cover Material: As described in "Client's Identification".

Standard Substrate Material: Non FR polyurethane foam, density 1.8 ± 0.05 lb/ft³

BRIEF DESCRIPTION OF TEST: Miniature cushions are prepared using the client's cover fabric over the standard filling material. The vertical or back cushions measure 8" x 8" x 2". The horizontal or seat cushions measure 8" x 5" x 2".

A lighted cigarette is placed in the crevice formed by the vertical cushion and the horizontal cushion.

The test is terminated at 45 minutes if smoldering is no longer observed.

Test measurements and observations are recorded.

-- See Page 3 for "Results" and "Conclusion" --



Received:01/25/2018	Completed:01/26/2018	Letter: S2	BG	P.O.#: 18-0066208	Test Report #:	3-24249-0-02
Client's	Style: K2259 Cationc. Content: 30% Polyester, 70% Post Consumer Recycled Polyester. Finish: Greenshield & Acrylic					
Identification:	Backing. Weight: 23 oz/ly. End Use: Upholstery.					
Tested For: Sandra L. Gerloff			Key Test: CA TB 117-2013 (Section I-Cover			235
Knoll Inc.			Fabric) /ACT			
1235 Water Street			Tel: 1-(215)-679-1765		Ext:	
E Greenville, PA 18041			Fax: 1-(215)-679-1600			

PASS/FAIL/REPEAT CRITERIA: A material is considered to pass or fail based on the following criteria:

1. A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs:
 - a) The mock-up test specimen continues to smolder after the 45 minute test duration;
 - b) A vertical char length (measured as specified in step 11.9 of ASTM E1353-08a¹) of more than 1.8 inches (45 mm) develops on the cover fabric.
 - c) The mock-up test specimen transitions to open flaming.
2. The cover fabric passes the test if three initial mock-up specimens pass the test, i.e., the cigarettes burn their entire length and the mock-ups are no longer smoldering.
3. If more than one initial specimen fails, the cover fabric fails the test.
4. If any one of the three initial specimens fails, repeat the test on additional three specimens.
5. If all three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens fails, the cover fabric fails the test.

DISCUSSION: The current version of California Technical Bulletin 117-2013 has no provision to recognize cigarettes that self-extinguish prior to burning their entire length. However, ASTM E 1353 does recognize this phenomenon.

The Govmark report evaluates replacement cigarettes as follows:

If a cigarette self-extinguishes (SE) before burning its entire length, a new cigarette is placed into the test. If the new (replacement) cigarette self-extinguishes or burns its entire length, the result for that specimen will then be evaluated as if the cigarette burned its entire length when assigning the "Passing/Failure" conclusion.