Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

AWTA PRODUCT TESTING

| Client : | Woven Image Pty Ltd | Test Number | : | 16-006332 |
|----------|---------------------|-------------|---|------------|
| | 37-39 Chard Road | Issue Date | : | 21/12/2016 |
| | Brookvale NSW 2100 | Print Date | : | 22/12/2016 |

| Sample Description | Clients Ref : "Focus" | | | | |
|--------------------|--------------------------------------|---------|--|--|--|
| | Woven fabric with knitted scrim | | | | |
| | Colour : Purple | | | | |
| | Nominal Composition : 100% Polyester | | | | |
| | Nominal Mass per Unit Area/Density : | 380g/m2 | | | |

AS/NZS 3837-1998

Method of Test for Heat and Smoke Release Rates for Materials and Products using an Oxygen **Consumption Calorimeter**

| | | Specimer | ı | | |
|--------------------------------------|--------------------|---------------------|-------------------|------------------|-------|
| | 1 | 2 | 3 | Mean | |
| Average Heat Release Rate | 39.3 | 39.0 | 37.1 | 38.5 | kW/m² |
| Average Specific extinction area | 84.4 | 71.7 | 81.1 | 79.1 | m²/kg |
| | (according to Spec | cification C1.10 of | f the Building Co | de of Australia) | |
| Test orientation : Horizontal | | o | | | |
| | | Specimen | | | |
| | 1 | 2 | 3 | Mean | |
| Irradiance | 50 | 50 | 50 | 50 | kW/m² |
| Exhaust flow rate | 24 | 24 | 24 | 24 | L/sec |
| Time to sustained flaming | 66 | 55 | 68 | 63 | sec |
| Test duration | 311 | 320 | 340 | 324 | sec |
| Peak heat release after ignition | 129.6 | 98.8 | 123.8 | 117.4 | kW/m² |
| Average heat at 60 s | 85.0 | 71.8 | 90.6 | 82.5 | kW/m² |
| Average heat at 180 s | 47.9 | 50.2 | 48.7 | 48.9 | kW/m² |
| Average heat at 300 s | 39.6 | 39.3 | 37.4 | 38.8 | kW/m² |
| Total heat released | 9.6 | 10.3 | 10.1 | 10.0 | MJ/m² |
| Average effective heat of combustion | 6.4 | 6.6 | 6.4 | 6.4 | MJ/kg |

47198

16415

Australian Wool testing Authority Ltd Copyright - All Rights Reserved C



985

Accredited for compliance with ISO/IEC 17025 - Chemical Testing : Accreditation No - Mechanical Testing

Accreditation No

983

Page 1 of 8





Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA

Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results

relate only to the sample or samples tested. This document shall not be reproduced except in full and

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

AWTA Product Testing

| Client : | Woven Image Pty Ltd 37-39 Chard Road Brookvale NSW 2100 | | | ls | est Number : sue Date : rint Date : | 16-006332 21/12/2016 22/12/2016 | |
|-------------------|---|------|------|------|---|---------------------------------------|--|
| Initial thickness | | 7.0 | 7.0 | 7.0 | 7.0 | mm | |
| Initial mass | | 86.6 | 88.1 | 89.3 | 88.0 | g | |
| Mass remaining |] | 72.6 | 74.7 | 75.2 | 74.2 | g | |
| Mass percentag | ge pyrolysed | 16.2 | 15.3 | 15.8 | 15.7 | % | |
| Mass loss | | 14.0 | 13.4 | 14.1 | 13.8 | g | |
| Average rate of | mass loss | 6.2 | 5.9 | 5.8 | 6.0 | g/m².s | |

These test results relate only to the behaviour of the product under the conditions of the test, they are not intended to be the sole criterion for assessment of performance under real fire conditions.

The results of these fire tests may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of the fire hazard under all fire conditions.

Samples were loose laid onto a substrate of 6mm thick cement sheeting prior to testing.

Tests were conducted with a wire grid placed over the sample during testing. This was done to contain intumescing sample within the sample holder.

47198

Australian Wool testing Authority Ltd Copyright - All Rights Reserved

16415



AWTA

results

985

Accredited for compliance with ISO/IEC 17025 - Chemical Testing - Mechanical Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated

Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test

relate only to the sample or samples tested. This document shall not be reproduced except in full and

: Accreditation No Accreditation No 983

Page 2 of 8



JACKSON B.Sc.(Hons) ANAGING DIRECTOR



C

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499


TEST REPORT

Client : Woven Image Pty Ltd 37-39 Chard Road Brookvale NSW 2100
 Test Number
 :
 16-006332

 Issue Date
 :
 21/12/2016

 Print Date
 :
 22/12/2016





JACKSON B.Sc.(Hons)

ANAGING DIRECTOR

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031


P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Woven Image Pty Ltd 37-39 Chard Road Brookvale NSW 2100

Test Number : 16-006332 **Issue Date** 21/12/2016 : **Print Date** 22/12/2016 :



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051


Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Woven Image Pty Ltd 37-39 Chard Road Brookvale NSW 2100
 Test Number
 :
 16-006332

 Issue Date
 :
 21/12/2016

 Print Date
 :
 22/12/2016



APPROVED SIGNATORY

ANAGING DIRECTOR

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031


P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Woven Image Pty Ltd 37-39 Chard Road Brookvale NSW 2100

Test Number : 16-006332 **Issue Date** 21/12/2016 : **Print Date** 22/12/2016 :



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499


TEST REPORT

Client : Woven Image Pty Ltd 37-39 Chard Road Brookvale NSW 2100
 Test Number
 :
 16-006332

 Issue Date
 :
 21/12/2016

 Print Date
 :
 22/12/2016

Specimen: 3



JACKSON B.Sc.(Hons)

ANAGING DIRECTOR

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031


P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Woven Image Pty Ltd 37-39 Chard Road Brookvale NSW 2100

Test Number : 16-006332 **Issue Date** 21/12/2016 : **Print Date** 22/12/2016 :





Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

Group Number Assessment

(In accordance with AS 5637.1-2015)

This is to confirm that the product as described below has been tested by AWTA Product Testing .

Testing was performed in accordance with AS/NZS 3837-1998 Method of test for heat and smoke release rates for materials and products using an oxygen consumption calorimeter.

| Test Sponsor : | Woven Image Pty Ltd | Test Number | : | 16-006332 |
|----------------|---------------------|-------------|---|------------|
| | 37-39 Chard Road | Issue Date | : | 21/12/2016 |
| | Brookvale NSW 2100 | Print Date | : | 22/12/2016 |

| Sponsor Product | Clients Ref : "Focus" Woven fabric with knitted scrim |
|-----------------|---|
| | Colour : Purple Nominal Composition : 100% Polyester Nominal Mass per Unit Area/Density : 380g/m2 |

| Product Group Number Classification : | 1 | |
|---------------------------------------|------|-------|
| Average Specific Extinction Area : | 79.1 | m²/kg |

Chris Campbell Client Relations Manager

The message/document(s) contained in this electronic attachment is intended for the party to which it is addressed and may contain confidential information or be subject to professional privilege. It's transmission is not intended to place the contents into the public domain.

If you have received this transmission in error, it's disclosure or copying is prohibited. Please contact us by collect call so that arrangements can be made at our expense to rectify the error.