

EchoPanel® Palace

Designer: Woven Image

Application(s): Walls, Partitions

Composition & Pattern

Composition 100% PET (60%-80% post-consumer recycled)*

Colours Available 32

Pattern Type Precision Cut

Additional Information *As part of our ongoing commitment to sustainability, we are increasing the amount of post-consumer PET in EchoPanel 12mm, from 60% to 80%. We anticipate all stock to have transitioned by January 2025.

Dimensions & Weight

Dimensions Length: 2750mm (+/-2mm) Width: 1100mm (+/-2mm) Thickness: 12mm (+/-7%)

Unit of Sale Panel

Unit of Sale Net Weight (kg) 7.1

Performance

Fire Test Result AS 1530.3, ISO 9705: Group 1, BS EN 13501.1: Classification B - s1, d0, ASTM E84 Unadhered: Class 1 or A, GB 8624 B1, BS EN 45545-2

+ A1 Annex C: CIT: 0.05

| | |
|---|---|
| Acoustic Performance Standard Test Method | AS ISO 354: 2006 (R2016), ASTM C423 - 17, AS ISO 11654: 2002 (2016) |
| Noise Reduction Coefficient (NRC) Result | Direct fix: 0.45, 20mm air gap: 0.60, 50mm air gap: 0.75 |
| Sound Absorption Average (SAA) Result | Direct fix: 0.43, 20mm air gap: 0.61, 50mm air gap: 0.75 |
| Weighted Sound Absorption Coefficient (α_w) Result | Direct fix: 0.30 (MH), 20mm air gap: 0.45 (MH), 50mm air gap: 0.60 (MH) |
| Sound Absorption Class | D (Direct fix), D (20mm air gap), C (50mm air gap) |
| Additional Acoustic Information | Noise reduction coefficient result key: H = High Frequency / MH = Mid to High Frequency |
| Colour Fastness to Light Standard Test Method | ISO 105 B02 |
| Colour Fastness Light Rating | 6 - 7 |

Sustainability

VOC Emissions Results ASTM D5116 - 2017: TVOC Emissions Rate: 0.033mg/m²/hr (24hrs); Formaldehyde Emissions Rate: 0.07mg/m²/hr. CDPH Standard Method v1.2 - 2017 (CA 01350): TVOC Emissions Rate: 0.013mg/m³; Formaldehyde Emissions Rate: <1µg/m³

Sustainability Performance





Instructions

Additional Information See Woven Image EchoPanel® Care & Cleaning Guide.
See Woven Image EchoPanel® Precision Cut Panels Installation Guide.

Exact colour matching cannot be guaranteed between batches.
Fibre mix and web variation are natural characteristics of this product.