

Pico Embossed Panel

Designer: Woven Image

Application(s): Walls

Composition & Pattern

Composition 100% PET (51% recycled)

Colours Available 25

Pattern Type Embossed

Dimensions & Weight

Dimensions Length: 2800mm (+/-3 mm), Width: 1130mm (+/- 3mm), Thickness: 9mm (+/- 7%)

Unit of Sale Panel

Unit of Sale Net Weight (kg) 8.13

Performance

Fire Test Result ASTM E84 Unadhered: Class 1 or A, BS EN 13501.1: Classification B - s1, d0, ISO 9705: Group 1

Acoustic Performance Standard Test Method AS ISO 354: 2006 (R2016), AS ISO 11654: 2002 (2016), ASTM C423 - 17

Noise Reduction Coefficient (NRC) Direct fix: 0.30, 20mm air gap: 0.50, 50mm air gap: 0.70.

Result	Achieves an NRC of 0.75 with a 18mm acoustic backing
Weighted Sound Absorption Coefficient (αw) Result	Direct fix: 0.20 (H), 20mm air gap: 0.35 (MH), 50mm air gap: 0.60 (MH). Achieves an αw of 0.75 with a 18mm acoustic backing
Sound Absorption Class	E (Direct fix), D (20mm air gap), C (50mm air gap)
Additional Acoustic Information	Noise reduction coefficient result key: H = High Frequency / MH = Mid to High Frequency
Colour Fastness to Light Standard Test Method	ISO 105 B02
Colour Fastness Light Rating	6
Colour Fastness to Rubbing Standard Test Method	ISO 105 - X12
Colour Fastness to Rubbing Rating	Wet: 4 - 5, Dry: 5

Sustainability

VOC Emissions Results ASTM D5116: TVOC Emissions Rate: 0.015mg/m²/hr (7 days), and CDPH Standard Method v1.2: TVOC Emissions Rate: 0.010mg/m³; Formaldehyde Emissions Rate: <5µg/m³

Sustainability Performance



Declare.



Instructions

Additional Information See Woven Image Embossed Panels Care & Cleaning Guide, and Installation Guide.

Exact colour matching cannot be guaranteed between batches. Fibre mix and web variation are natural characteristics of this product.

To assist in accurate pattern matching on a continuous wall, PICO has been trimmed on all four sides with a unique 5 degree bevel. Please refer to installation guide for more information. Dimensions shown in millimetres.

